



CLEAR COAT FOR CONCRETE

ENGINEERING DATA SHEET

PRODUCT DESCRIPTION

Rust Bullet Clear Coat for Concrete is a clear, high gloss, anti-skid coating designed as a topcoat for Rust Bullet for Concrete. Use Clear Coat for Concrete to create an anti-skid finish, seal decorative flake, increase traction, and provide extra protection to concrete surfaces. Its ridged profile offers aggressive anti-skid characteristics in a one component, one-step application. Clear Coat for Concrete provides long lasting protection against grease, oils, chemicals, abrasion, scratching and hot tire pickup; Typical application method is a 3/8" nap roller, however, a brush may also be used.

TYPICAL USES

Rust Bullet Clear Coat for Concrete is designed specifically as a top coat for the Rust Bullet for Concrete Coating on concrete floors including garages, walkways, patios and much more, providing a safe slip resistant surface.

ADVANTAGES

- Water Clear Finish
- Anti-Skid Protection
- Single Component
- Excellent Resistance to Weather and Mechanical Abuse
- Excellent Chemical and Road Salt Resistance
- No Hot Tire Pickup
- Excellent UV resistance; Non-Yellowing
- Self-Leveling
- No Peeling or Flaking

SPECIFICATIONS

- **Weight per gallon:** 8.25 – 8.5 lb.
- **Pigment Type:** None
- **Flash Point:** 110°F
- **VOC:** 316 g/liter
- **Viscosity:** 220 - 320 cP
- **Theoretical coverage:** 350-400 ft²/ gal. Depending on surface.
- **Solids by weight:** 69% ± 2%
- **Recommended WFT:** 2-4 mils (applied in 1-2 wet coats)
- **Temperature Resistance:** Continuous 314°F
- **Chemical Resistance:** Excellent
- **Recoatibility:** With Clear Coat for Concrete after 2-6 hours, not to exceed 12 hours.
- **Color/Finish:** Clear Gloss Anti-Skid
- **Cure Time:** Depending on ambient temp and relative humidity, and WFT.
 - Handle: 2-4 Hours;
 - Touch: 2-4 hours.
 - Recoat: 2-6, not exceeding 12 hours.
- **Shelf Life:** 2 years, unopened, stored between 50°-100°F.
- **Application Temperature:** 32°F-110°F (0°C-43°C)
- **Compatibility:** With most other MCUs (Moisture-cured Urethane); always refer to the coating manufacturers guidelines for application and compatibility

SAFETY INFORMATION

Avoid ingestion, contact with skin or eyes. The use of safety glasses and chemical gloves is recommended. When brushing, rolling or spraying, appropriate NIOSH approved respiratory protection is recommended. See [Safety Data Sheet](#) for complete safety data before use, available at www.RustBullet.com. It is the applicator's responsibility to understand these safety precautions and the work environment, to protect themselves and/or others.

SURFACE PREPARATION

Rust Bullet Clear Coat for Concrete should be applied within 12 hours of the last coat of Rust Bullet for Concrete. If within this 12 hours, no additional surface preparation should be necessary. If more than 12 hours has lapsed, the previous coat should be allowed to cure for 24 hours and then lightly scuffed using 150 grit. For more information contact us at:

Rust Bullet, LLC ~ 300 Brinkby Avenue, Suite 200, Reno, NV 89509 USA 1(800) 245-1600, 1(775) 829-5606 www.RustBullet.com

LIMITATION OF LIABILITY

All recommendations or suggestions relating to the use of the product, whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge is reliable. The product and information is designed for users having the requisite knowledge and industrial skills, and the end-user has the responsibility to determine the suitability of the product for its intended use. Conditions of use are beyond our control, Rust Bullet, LLC (the Company), disclaims any liability incurred in connection with the use of our products and information contained herein. No person is authorized or empowered to make any statement or recommendation not contained herein, any such statement or recommendation so made shall not bind The Company. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents Rust Bullet, LLC has no control over either the quality of condition of the substrate, or the many factors affecting the use and application of the product. Therefore, Rust Bullet, LLC does not accept any liability arising from loss, injury, or damage resulting from such use or the contents of this data sheet. The information contained in this data sheet is subject to modification as a. This data sheet replaces and annuls all previous issues and the user has the responsibility to ensure that this sheet is current prior to using the product. 4/17 am